



PRODUCT INFORMATION

DEFTOIL MARINE TEAKWOOD

PENETRATING OIL

DESCRIPTION: DEFTOIL MARINE TEAKWOOD is Exterior Penetrating Danish Oil SPECIFICALLY FORMULATED FOR HARDWOODS, SUCH AS TEAK. It is designed as a fine wood penetrating sealer to protect wood against the detrimental effects of water and other environmental hazards. The protective oils and polymerizing resin soaks into dried and water damaged wood fibers and reinforces the cell structure. DEFTOIL MARINE TEAKWOOD contains mildewcides.

SPECIFICATIONS

<p>SOLVENT TYPE Mineral Spirits</p> <p>RESIN TYPE Linseed Oil, Long Oil Alkyd</p> <p>FINISH Very low sheen when applied to bare wood.</p> <p>COLORS Natural</p> <p>BASES Not available</p> <p>VISCOSITY AT 77° F (25° C) 19 - 21 sec. EZ#2 (Zahn Cup)</p> <p>VOC CONTENT 250 g/L. Meets the Federal AIM Rule.</p> <p>SOLIDS BY VOLUME SOLIDS BY WEIGHT 68 ± 1 % 72 ± 1 %</p> <p>WEIGHT PER GALLON 7.3 – 7.6</p> <p>COMPOSITION BY WEIGHT Vehicle 72 % Solvent and additives 28 %</p> <p>RECOMMENDED FILM THICKNESS PER COAT Since all DEFTOIL MARINE TEAKWOOD has to penetrate the wood, the film thickness has no significance, and cannot be measured.</p> <p>PRACTICAL COVERAGE PER COAT AT THE RECOMMENDED DRY FILM THICKNESS 400-500 sq.ft./gal., depending on surface conditions.</p> <p>AVERAGE DRY TIME AT 77° F (25° C) 30 minutes after rubbing into the wood, the surface is dry. It takes at least a week to develop water resistance.</p> <p>APPLICATION EQUIPMENT Cloth, Brush, Airless Spray, HVLP Spray, Conventional Spray</p> <p>PACKAGING Quarts, Gallons</p>	<p>MATERIAL SAFETY DATA SHEET Available on request</p> <p>SURFACE PREPARATION All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, and other contaminants. Remove all loose, peeling, or cracked coatings. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded, and cleaned. Since DEFTOIL MARINE TEAKWOOD has to penetrate the wood surface, it cannot be applied to a sealed surface. Sand any coating off completely to the bare wood.</p> <p>THINNING RECOMMENDATIONS DEFTOIL MARINE TEAKWOOD is supplied at application viscosity. Thinning is not recommended. In VOC (Volatile Organic Compound) regulated areas it is not permitted to add additional solvent.</p> <p>APPLICATION Shake well. Apply liberal amount over surface. After 30 minutes wipe off all excess. Do not allow any excess material to dry on the surface. <u>Wipe surface completely dry.</u> Read warning below about rags disposal.</p> <p>CLEANUP Use Mineral Spirits for cleanup. Dispose of waste in accordance with applicable laws and regulations.</p> <p>OTHER SYSTEM INFORMATION DEFTHANE, Oil Modified Urethane Varnish, can be applied over DEFTOIL MARINE TEAKWOOD, when more protection is desired, or a higher gloss appearance is needed.</p> <p>SPONTANEOUS COMBUSTION Rags, steel wool or other waste soaked with DEFTOIL MARINE TEAKWOOD may spontaneously catch fire if improperly discarded. IMMEDIATELY AFTER USE, place rags, steel wool or other waste in a sealed water filled container. Add a liquid detergent to the water to wash out the oil. Spread out all waste material in a single layer, to let it dry, while the heat developed can escape.</p> <p>WARNING COMBUSTIBLE. DEFTOIL MARINE TEAKWOOD contains Mineral Spirits, a combustible solvent. Provide adequate ventilation and avoid all ignition sources during application and drying.</p>
---	---